

DuPont™ Tyvek® FireCurb® breather membrane

Technical Datasheet



Application: Flexible sheets for water proofing – Part 2: Underlays for walls EN 13859-2: 2010

Style name **2066B** Language **English**
 Type of carrier **flash-spun-bond HDPE with transparent halogen-free flame retardant acrylic lacquer** Applicable for **UK, Ireland**

PROPERTY	METHOD	UNITS	NOMINAL	MINIMUM	MAXIMUM
FUNCTIONALITY: WATER VAPOUR TRANSMISSION, WATER TIGHTNESS, WEATHER DURABILITY, FIRE CLASS					
Reaction to fire *	EN 13501-1	class	B-s1,d0	-	-
Water vapour transmission (sd)	EN ISO 12572 (C)	m	0,015	0,005	0,025
Temperature resistance	-	°C	-	-40	+100
Flexibility at low temperature	EN 1109	°C	-	-	-40
UV exposure	-	months	-	-	4
Product- / Functional layer thickness	-	mm	0,175 / 0,175	-	-
Water tightness	EN 1928 (A)	class	W1	-	-
Water column	EN 20811	m	1,4	-	-
PHYSICAL AND MECHANICAL PROPERTIES					
Mass per unit area	EN 1849-2	g/m²	68	62	74
Maximum tensile force (MD)	EN 12311-1	N/50mm	275	230	320
Elongation at max. tensile force (MD)	EN 12311-1	%	15	10	20
Maximum tensile force (XD)	EN 12311-1	N/50mm	275	225	325
Elongation at max. tensile force (XD)	EN 12311-1	%	18	11	25
Resistance to tearing MD (nail shank)	EN 12310-1	N	41	25	57
Resistance to tearing XD (nail shank)	EN 12310-1	N	36	21	52
PROPERTIES AFTER AGEING					
Artificial ageing by UV and heat:	EN 1297 & EN 1296				
Water tightness	EN 1928 (A)	class	W1	-	-
Maximum tensile force (MD)	EN 12311-1	N/50mm	225	180	270
MD elongation at max. tensile force	EN 12311-1	%	10	6	14
Maximum tensile force (XD)	EN 12311-1	N/50mm	225	175	275
XD elongation at max. tensile force	EN 12311-1	%	12	7	17
ADDITIONAL PROPERTIES					
Length (customer related, expressed in m)	EN 1848-2	deviation in %	0	0	-
Width (customer related, expressed in mm)	EN 1848-2	deviation in %	0	-0,5	+1,5
Straightness	EN 1848-2	mm/10m	-	-	30
Dimensional stability (MD & XD)	EN 1107-2	%	-	-	1
Resistance to penetration of air	EN 12114	m³/(m² h 50Pa)	-	-	2
Windtight	-	-	yes	-	-

(*): installed on mineral wool, mineral fiber boards or freehanging: B-s1,d0 / installed on wood: D-s2,d2

The product mentioned above, in our opinion, fulfils the criteria of being classified as 'article' (REACH, Art. 3.3). There are no substances intended to be released from this product under normal or reasonably foreseeable conditions of use. The above article to our current knowledge does not contain substances, above the legal threshold, that are on the 'Candidate List' of Substances of Very High Concern (SVHC) as published on the ECHA website.



Effective date: 15/12/2023
 First CE: 29/10/2012

EC-CERTIFICATE OF CONFORMITY
 0799-CPR-128

DuPont (UK) Limited
 HERE,
 470 Bath Road, Arnos Vale,
 Bristol, BS4 3AP
 tyvek.construction@dupont.com
 Tel +44 (0) 117 452 9050

Some test methods are modified according to the EN 13859-2: 2010 and/or according to the DuPont ISO 9001:2015 certified quality system (for details please contact your regional DuPont representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.

www.building.dupont.co.uk